

## DECLARATION

I declare that this thesis is, to the best of my knowledge, a presentation of my original research work. Wherever contributions of others are involved, every effort is made to indicate this clearly with due reference to the literature. I certify that I have complied with the rules, requirements, procedures and policy of the University. I therefore cede copyright of the thesis in favour of the Universiti Malaysia Perlis.

**17<sup>th</sup> July 2014**  
(0830410275)

MOHD RADZI BIN ALI

© This item is protected by original copyright

## ACKNOWLEDGEMENTS

In the name of Allah, the Most Gracious and the Most Merciful. Alhamdulillah, all praises to Allah for his blessing and the strength that was bestowed upon me to complete this research project.

First of all, I would like to thank Universiti Malaysia Perlis and Dr Khairul Rafezi Ahmad as Dean School of Material Engineering for receive as a student and do my master study. Exclusively to the School of Materials Engineering, I would like to express my gratitude for granting me unlimited access to the state of the art analytical instruments and for providing a very conducive research facility.

Special thanks go to my supervisor Prof. Dr. Shamsul Baharin Jamaludin for his constant guidance and support. I would like to express my appreciation for your undying supports and also to lecturer Prof. Madya. Che Mohd Ruzaidi Ghazali and Mr Shaiful Rizam Shamsudin Not to forget, all the teaching engineer and technicians of the School of Materials Engineering Mr Azmi Kamardin, Mr Tajuddin Idris, Mr. Chek Idrus Bin Omar, Mr. Azmi Bin Aziz, Mr. Ahmad Hadzrul Iqwan Bin Jalaluddin, Mr. Mohd Nasir Bin Ibrahim, Mr. Ku Hasrin Bin Ku Abdul Rahman, Mr. Zaidi Bin Zainol and Mr. Rosmawadi Bin Othman. I would also like to express all my friends for all their support and give useful information to helping me to end up this project

Finally, a special thanks to my beloved parents for fully support and never stop and guide me along the correct path of education with much scarification and determination. Exclusive thanks to my lovely wife Pn. Nurul Akma Bt Tajuddin and to my children Nur Auni Raudhah and Muhammad Ammar Rizqi for fully support and give me time to finish this thesis. May Allah bless to all of you.

## KESAN KOMPOSISI ABU SAWIT KEPADA APLIKASI PAD BREK

### ABSTRAK

Penggunaan bahan gentian asbestos sebagai bahan pengisi di dalam pad brek telah dielakkan kerana ia mempunyai sifat-sifat karsinogenik yang mungkin menyebabkan risiko kesihatan. Asbestos kini telah digantikan dengan campuran gentian alternatif seperti gentian mineral, selulosa, aramid, pan, kaca dicincang, keluli dan gentian logam lain. Kajian ini dijalankan bagi menghasilkan pad brek tanpa asbestos. Sampel komposit untuk penggunaan pad brek disediakan melalui pra-campuran abu kelapa sawit,  $\text{CaCO}_3$ , resin fenolik,  $\text{Al}_2\text{O}_3$ , grafit dan gentian logam. Kemudian, bahan-bahan ini dipadatkan dengan menggunakan pemampat sejuk/ mesin manual mampatan. Ujian sifat mekanik seperti seperti ujian mampatan dan kehausan telah dijalankan. Keputusan menunjukkan bahawa komposisi peratusan tinggi abu kelapa sawit mempunyai kekuatan mampatan yang lebih baik. Nilai tertinggi untuk untuk kekuatan mampatan adalah 14.93 MPa dan nilai yang paling rendah adalah 8.85 MPa. Keputusan bagi ujian kehausan menunjukkan bahawa kehilangan jisim yang tertinggi adalah  $0.2803 \text{ m}^3$  untuk peratusan rendah abu kelapa sawit manakala kehilangan jisim yang terendah adalah  $0.00969 \text{ m}^3$  bagi peratusan tinggi abu kelapa sawit. Komposisi tanpa asbestos menunjukkan sifat-sifat mekanik yang setanding dengan pad brek konvensional.

## EFFECT OF PALM ASH COMPOSITION TO THE BRAKE PAD APPLICATION

### ABSTRACT

The asbestos fibre as a filler material in brake pad has been avoided due to its carcinogenic nature that might cause health risks. Asbestos has now been replaced by a mix of alternative fibres such as mineral fibres, cellulose, aramid, PAN, chopped glass, steel and other metal fibre. This research was conducted to produce a non-asbestos brake pad. In this research, palm ash was used to replace asbestos. The composite samples for brake pad application were developed by pre-mix the palm ash,  $\text{CaCO}_3$ , phenolic resins,  $\text{Al}_2\text{O}_3$ , graphite and steel fibre mill. Then, the material was compacted by using cold press/manual press machine. The physical and mechanical testing such as compression and wear test was carried out in this research. Results indicated that the higher percentage composition of palm ash has better compressive strength. The highest value for compressive strength is 14.93 MPa and the lowest value is 8.85 MPa. Wear test result indicated that the highest mass loss value is 0.2083  $\text{m}^3$  for the lowest percentage palm ash whereas the lowest mass loss is 0.00969  $\text{m}^3$  for the highest percentage of palm ash. The composition of non-asbestos showed comparable mechanical properties with conventional brake pads

## TABLE OF CONTENT

	<b>PAGE</b>
<b>APPROVAL AND DECLARATION SHEET</b>	ii
<b>ACKNOWLEDGEMENT</b>	iii
<b>ABSTRAK</b>	iv
<b>ABSTRACT</b>	v
<b>TABLE OF CONTENT</b>	vi
<b>LIST OF TABLES</b>	x
<b>LIST OF FIGURES</b>	xi
<b>LIST OF ABBREVIATIONS</b>	xiii
<b>CHAPTER 1: INTRODUCTION</b>	
1.1 Research Background	1
1.2 Problem Statement	2
1.3 Objectives	4
1.4 Scope of The Project	5
<b>CHAPTER 2: LITERATURE REVIEW</b>	
2.1 Brake Pad	6
2.2 Fibre	11
2.3 Binder	13
2.4 Fillers and Reinforcements	14
2.5 Abrasive	16
2.6 Palm Ash	17
2.7 Phenolic	18

2.8	Aluminium oxide	20
2.9	Calcium carbonate	20
2.10	Steel fibre	21
2.11	Graphite	22

### **CHAPTER 3: RESEARCH METHODOLOGY**

3.1	Introduction	24
3.2	Design Experiments	24
3.2.1	Phase 1 – Raw Material Characterisation.	26
3.2.1.1	Particle Size Distribution Analysis	26
3.2.1.2	Morphology raw materials	27
3.2.1.3	Thermo gravimetric Analysis (TGA)	27
3.2.2	Phase 2 – Sample Processing	28
3.2.2.1	Mixing	28
3.2.2.2	Compaction	29
3.2.2.3	Curing and Post-Cure	29
3.2.3	Phase 3 – Physical and Mechanical Testing	31
3.2.3.1	Density and porosity analysis	31
3.2.3.2	Porosity	32
3.2.3.3	Water absorption analysis	33
3.2.3.4	Impact test	34
3.2.3.5	Compression Test	34

3.2.3.6 Hardness Test	35
3.2.3.7 Wear test (Pin-on-Disk Method)	35
3.2.2.8 Microstructural analysis	38

## **CHAPTER 4: RESULT AND DISCUSSION**

4.1	Introduction	39
4.2	Analysis of raw materials	39
4.2.1	Particle size analysis	39
4.2.2	Microstructural analysis of raw materials	42
4.2.3	SEM-EDS Analysis	45
4.2.4	Thermo gravimetric Analysis (TGA)	49
4.3	Characterization of Physical Properties	50
4.3.1	Density and porosity	50
4.3.2	Water Absorption Analysis	52
4.3.3	Izod Impact test	53
4.3.4	Microstructural Analysis	54
4.3.5	Compression Test	56
4.3.6	Hardness Test	57
4.3.7	Wear test	59
4.3.7.1	Applied load 10N	59
4.3.7.2	Applied load 20N	63
4.3.7.3	Applied load 30N	66
4.3.7.4	Morphology of worn surface under SEM	69

4.3.7.4.1 Sliding distance (3000 m) Load (10N)	69
4.3.7.4.1 Sliding distance (3000m) Load (20N)	71
4.3.7.4.1 Sliding distance (3000m) Load (30N)	73

## **CHAPTER 5: CONCLUSION AND RECOMMENDATION FOR FUTURE PROJECT**

5.1 Conclusion	76
5.2 Recommendation For Future Project	77

<b>REFERENCES</b>	84
-------------------	----

<b>LIST OF PUBLICATIONS</b>	82
-----------------------------	----

<b>APPENDIX A</b>	83
-------------------	----

<b>APPENDIX B</b>	83
-------------------	----

<b>APPENDIX C</b>	84
-------------------	----

<b>APPENDIX D</b>	84
-------------------	----

<b>APPENDIX E</b>	85
-------------------	----

<b>APPENDIX F</b>	85
-------------------	----

© This item is protected by original copyright



## LIST OF TABLE

NO.		PAGE
2.1	Historical Composition of Automotive Friction Brake Materials	7
2.2	Previous non-asbestos Brake Pad composition	11
2.3	Various Fibres Used in Brake Pads	12
2.4	Type of Binder Used in Brake Pads	13
2.5	Fillers and Reinforcements	14
2.6	Abrasive Elements	16
2.7	Advantages of Phenolic Resin	19
2.8	Physical properties of metal fibre	22
3.1	Composition of the samples	29

## LIST OF FIGURES

NO.		PAGE
3.1	Flow chart of experiment	25
3.2	Position of the pin and disk in wear test according ASTM 99 – 95a (ASTM G 99, 2004)	36
4.1	Particle size distribution of Phenolic	40
4.2	Particle size distribution of Aluminium Oxide	41
4.3	Particle size distribution of CaCO <sub>3</sub>	41
4.4	Particle size distribution of Graphite	41
4.5	SEM micrograph of Palm ash	42
4.6	SEM micrograph of CaCO <sub>3</sub>	43
4.7	SEM micrograph of phenolic powder	43
4.8	SEM micrograph of Al <sub>2</sub> O <sub>3</sub> powder	44
4.9	SEM micrograph of graphite powder	44
4.10	SEM micrograph of steel fibre	45
4.11	EDS Palm ash	46
4.12	EDS Phenolic	46
4.13	EDS Graphite	47
4.14	EDS CaCO <sub>3</sub>	47
4.15	EDS Steel fibre	48
4.16	EDS Al <sub>2</sub> O <sub>3</sub>	48
4.17	TGA curve of palm ash	49
4.18	TGA curve of CaCO <sub>3</sub>	50

4.19	Density of the samples with different percentage of palm ash	51
4.20	Porosity of the samples with different percentage of palm ash	52
4.21	Water Absorption of the samples with different percentage of palm ash	53
4.22	Impact strength of brake pad sample with different percentage of palm ash	54
4.23	SEM micrograph of the brake pad samples with different percentage of palm ash	55
4.24	Compressive strength of the samples with different percentage of palm ash	57
4.25	Rockwell hardness result of the samples with different percentage of palm ash	58
4.26	Effect of sliding distance at constant load of 10N	60
4.27	Shows the stereomicroscope morphology of different percentage palm ash at 3000m sliding distance	62
4.28	Effect of sliding distance at constant load of 20N	64
4.29	Shows the stereomicroscope morphology of different percentage palm ash at 3000m sliding distance	65
4.30	Effect of sliding distance at constant load of 30N	67
4.31	Shows the stereomicroscope morphology of different percentage palm ash at 3000m sliding distance	68
4.32	Shows the SEM morphology of different percentage palm ash at 3000m sliding distance and 10N load at 100X magnification	70
4.33	Shows the SEM morphology of different percentage palm ash at 3000m sliding distance and 20N load at 100X magnification	72
4.34	Shows the SEM morphology of different percentage palm ash at 3000m sliding distance and 30N load at 100X magnification	74

## LIST OF ABBREVIATIONS

Al <sub>2</sub> O <sub>3</sub>	Aluminum Oxide
ASTM	America Society for Testing and Material
BaSO <sub>4</sub>	Barium Sulfate
Ca	Come after
CaCO <sub>3</sub>	Calcium Carbonate
CNSL	Cashew Nut Shell Liquid
EPA	Environmental Potential Agency
FASi	Fly Ash silica
Fe <sub>2</sub> O <sub>3</sub>	Hematite
Fe <sub>2</sub> O <sub>4</sub>	Magnetite
MPa	Mega Pascal
MPOB	Malaysia Palm Oil Board
NAO	Non Asbestos Organic
OPC	Ordinary Portland cement
OPA	Oil Palm Ash
P/M	Powder Metallurgy
Psi	Precipitated silica
RPM	Rotational Per Minute
S/S	Solidification/Stabilization
SEM	Scanning Electron Microscopy
SEM-EDX	Energy-dispersive X-ray spectroscopy
SiO <sub>2</sub>	Silica Oxide

TGA	Thermogravimetric Analysis
UCS	Unconfined Compressive Strength
US	United State
UTM	Universal Testing Machine
XRF	X-ray fluorescence
ZnO	Zinc Oxide
ZrSiO <sub>4</sub>	Zirconium silicate

© This item is protected by original copyright

## CHAPTER 1

### INTRODUCTION

#### 1.1 Research Background

Brake pad is one of the important components in automotive application. Brake pads are steel backing plate with friction materials bound to the surface that faces the disc brake rotor. Brake pad works to slow the speed or stop the vehicle. Brake pad materials are generally considered as composites. Most of the automotive industries have used a variety of materials and processes to produce the high performance of brake pad. An improvement of grip, noise reduction, hardness, heat resistance and last longer is a major role in producing brake pad. In addition, improvements in term of material used are important to reduce the cost. Numbers of different materials are used and almost more than 10 types of raw materials are involved in producing the brake pad (EL-Tayeb & Liew, 2009). Most material used for the production of brake pad is asbestos, ceramic, calcium carbonate, metals, graphite, phenolic, fibre and more. Each material has a special and important role in the production of brake pad. The types of materials for developing brake pad can generally be classified into five types of materials, depending on the specific functional requirement. These include fibres (Jie Fei et al. 2010), fillers (Kumar & Bijwe, 2011), binders (Ingo et al. 2004), friction modifier (Gurunath & Bijwe, 2007) and solid lubricants (Seong & Ho Jang, 2000).

## 1.2 Problem Statements

Asbestos is popular and widely used in fabrication of brake pads due to low price, excellent thermal stability, miscibility, tribological properties and its heat resistance (Gopal et al. 1996). However, it is well known that asbestos can degrade to airborne fibres (diameter less than 2  $\mu\text{m}$ ) and result in a long term health problem to human and environment which it can contribute to lung disease (Ho et al. 2005). Due to health issues as well as requirement for better quality, many countries have taken safety to stop using it for brake pad. Many material formulations of free asbestos brake pad were introduced such as in the U.S in the late end of the year 1960. Regarding these changes, there is still no clear explanation on this material consumerism. Beginning in mid-1970, three important new requirements were imposed on the automotive industry by the Federal Braking Regulations. One of them is the need to eliminate asbestos from friction materials (Mustafa Boz & Adem Kurt, 2007).

In this study, the asbestos in brake pad formulation is replaced with waste materials, which are palm ash. It is expected that recycle material can reduce the cost of the brake pad. In addition, it can recycle the palm ash that has a bigger amount waste in Malaysia. It was reported that palm ash has been used as cement replacement material and as an absorbent for the removal of zinc from aqueous solution (Chu & Hashim, 2003). Malaysia is the largest produced palm oil and it is a contributor to the economy of Malaysia and also palm oil in this country has contributed half of the world's palm oil production to increase global demand for vegetable oil (Basri et al. 1998). Therefore, all wastes produced from palm oil production become an alternative agent in the internal combustion chamber to

replace the fuel for electric power generation. After burning, the palm ash is produced and this ash cannot be used for other processes. The problem is to dispose the palm ash because it requires a relatively large area to collect the ashes and affecting the surrounding environment (Singh et al. 2010). In 2007, the Malaysian Palm Oil Board (MPOB) estimated the amount of Palm ash produced in Malaysia to be approximately 3 million tons (Chea Handara et al. 2010). To solve this problem, use of palm ash as a filler in a brake pad is a potential alternative to reduce the palm ash waste and reduce the costing of raw materials. From the literature, the utilization of palm ash as filler into brake pad material has not been investigated extensively. This project proposes to use palm ash as filler materials in brake pad.



### 1.3 Objectives

This research is carried out to study the brake pad formulation without using asbestos fibres. The relationship of the percentage composition of raw materials, different applied load and sliding distance are the main concern in this study.

The interest of the study includes:

- i. To formulate brake pad formulation using the palm ash as filler materials.
- ii. To study the physical and mechanical properties of the samples fabricated.
- iii. To investigate microstructure and to study the effect of palm ash addition on wear characteristic.

## 1.4 Scope of the Project

In this research, there are 3 major processes involve to produce the brake pad composites. In the usual production sequence first process (raw material characterization), analyse the raw material. The second process is sampling process; the sample formulation consists of phenolic powder as a binder, steel fibres as reinforcement, alumina ( $\text{Al}_2\text{O}_3$ ) as abrasive, graphite as a lubricant and, calcium carbonate ( $\text{CaCO}_3$ ) and palm ash as filler in the composition. The mixtures are compressed into the desired shape and followed by curing in a hot press machine to cause bonding of the particles into a hard rigid product. After that, samples were being post-cured again in the oven in several hours to fully cure. The third process is physical and mechanical testing. The wear loss behaviour has been tested on the samples. The ideal brake pad materials should have a constant of wear under various operating conditions such as applied load, sliding distance, time, temperature and speed.

## CHAPTER 2

### LITERATURE REVIEW

#### 2.1 Brake pad

Brake pad is an important component of all vehicles. It works to slow and to stop the vehicle. Brake pads in the brake callipers with their friction surfaces was contacting each other with the disc surface. In this situation, the contact will be producing heat and transfer a small amount of friction on the surface of the disc.

There are three broad classifications of friction material that have been used as brake pad materials which are organic, metallic and carbon.

1. Organic friction materials were exclusively composites of one or more binder resins, chrysotile asbestos fibre, and a blend of additives that modified friction, improved wear, reduced cost, and aided processing, change colour, and so on.

Currently, there are 3 subclasses of these resin-bonded friction materials:

- Asbestos, also called organic brake lining
- Non-asbestos organic (NAO), using a variety of fibres
- Semi metallic, or resin-bonded metallic

2. Metallic brake lining can be based on either copper or iron. Most are solid state sintered, often with inorganic additives to improve performance. Another metallic friction material is cast iron. Although this venerable material is used on some old railroad tread brakes, no new automotive applications are known to use cast iron as the brake lining. However, it remains a friction element, although not a brake lining (Arnold, 1992).
  
3. Carbon based brake linings, such as carbon-carbon, were developed for military and commercial aircraft disk brakes. Some are now used on racing cars where weight is critical, performance is demanding, and cost is secondary. Carbon-carbon friction materials are made from carbon fibre (also called graphite fibre) that bonds with amorphous carbon (Arnold, 1992). Table 2.1 shown Historical Composition of Automotive Friction Brake Materials.

**Table 2.1.** Historical Composition of Automotive Friction Brake Materials  
(Peter, 2001)

Material Description	Application (s)	Approximate Year
Cast iron on steel	Railroad car brake blocks and tires	Prior to 1870's
Hair and cotton belting (limited by charring at about 300°F)	Wagon wheels and early automobile	Ca. 1897
Woven asbestos with brass and other wires for increased strength and performance	Automobile and trucks	Ca. 1908
Moulded linings with shorter chrysotile	Automobile and trucks	Ca. 1926

fibre, brass particles, and low-ash bituminous coal		
Dry mix moulded material to replace cast iron brake blocks that produced metallic duct that shorted electric train rails	London underground	Ca. 1930
Flexible resin binders developed along with more complex formulations	Brake drum lining	1930's
Resin-bonded metallic brake linings	Industrial and aircraft applications	1950's
Glass fibres, mineral fibre, metal fibre carbon and synthetic fibre to provide semi-metallic with higher performance than asbestos (beginning of safety issue with asbestos)	Automotive and trucks	1960's
Non-asbestos (fibreglass) materials	Brake drums on original equipment cars	1980's
Suggested use of carbon fibre	Automotive brakes	1991
Palm ash, PCB, Phenolic and Aluminium	Brake pad	2011

Note: Ca. – come after

The effective performance of the brake pad friction at different levels of braking conditions in a wet environment is the main concerns of car drivers. Brake pad friction in the automotive brake system is always the key role of effective and safe braking performance, and blames always go to it when a brake-related problem arises. This is because brake pads are more vulnerable to various braking parameters. Therefore, frictional brake pad material should be designed to maintain a relatively high and stable friction coefficient irrespective of temperature, age, degree of wear, the presence of dirt, humidity, and water spraying from the road (Darius et al. 2007)

Over the past few years, many researchers have done research to reduce or replace the asbestos in the brake pad. Before it was banned by the United State in 1989 (Chan & Stachowiak, 2004). Asbestos is very important in manufacturing brake pad where it helps to structure the brake pad in the mechanical properties brake pad and gives more resistant to heat when it applied load to the friction. The asbestos can harm people and the environment. It occurs when the load applied to brake pad, the asbestos structure will disintegrate and it becomes light impurities and easily carried by air.

Asbestos is known to have toxicity. The inhalation of toxic asbestos fibres can cause serious illnesses, including malignant mesothelioma, lung cancer, and asbestosis (also called pneumoconiosis). Since the mid-1980s, many uses of asbestos have been banned in several countries. Asbestos that is used in previous brake pad had contained a carcinogen and are able to reach the alveolar area of the lung. In the safety profile, it confirmed human carcinogen producing lung tumours. Experimental neoplastigenic and tumorigenic data has been produced. Human pulmonary system effects by inhalation. Usually at least 4 to 7 years of exposure are required before serious lung damage (fibrous) results (Richard, 1991).

Asbestos exposure becomes a health concern when high concentrations of asbestos fibres are inhaled over a long time period. People who become ill from asbestos are almost always those who are exposed on a day-to-day basis in a job where they work directly with the material. As a person's exposure to fibre increases, either by breathing more fibres or by breathing fibre for a longer time, that person's risk of disease also increases. The disease is

very unlikely to result from a single, high-level exposure or from a short period of exposure to lower levels.

In the past decade, many automotive industries has phasing out the asbestos in brake pad. Each company has developed their own unique composition into safer alternative use, yet performing the very same task and claiming to better than others. The manufacture of brake pads must follow the demands such as (Chan & Stachowiak, 2004):

1. Not decompose or break down in such a way at high temperature.
2. Maintain a sufficiently high friction coefficient with the brake disc.
3. Exhibit a stable and consistent friction coefficient with the brake disc.

The percentage composition material control is very important to avoid significant impact on the mechanical properties of the brake pad (Peter, 2001). The ingredients in brake pad comprise fibre reinforcement, binder, friction modifiers, solid lubricant, abrasive, and filler. Fibre is usually used because of their friction properties, heat resistance, and their thermal conductivity. Besides that fibre can impart toughness and strength to the binder. Filler materials are added to improve or optimize the properties. Table 2.2 shows some of the previous study of the composition of the brake pad which contains fibre, filler, binder, friction modifier and lubricants.

**Table 2.2:** Previous non-asbestos Brake Pad (Darius et al. 2007)

Material	Function and Examples
Fibre	Provide rigidity, strength, thermal stability Steel wool, fibreglass, aramid, rock-wool, carbon
Filler	Low cost mineral to fill up the space Clay, calcium carbonate, barium sulphate, graphite
Binder	Hold the composition Phenol-formaldehydes, phenolic resin, rubber
Friction Modifier (Abrasive element)	Improve mechanical properties and wear characteristic Alumina, Zinc, aluminium trisulphide (cleanliness, abrasive), elastomer (wear characteristic)
Lubricants	Assist in part removal Copper sulphide, antimony trisulphide, graphite

Five main components of brake pads, the fibre, binders, fillers, friction and lubricant are substance that perform a variety of functions and can be placed in more than one classification.

## 2.2 Fibre

Fibre is one of the important elements in brake pad material to serve as reinforcement in the material which it affects the strength of the mechanical friction. From the work done by Chan & Stachowiak 2004 it has shown that the braking load is actually